

Pumadur DD Clear

Aliphatic Polyurethane UV Resistant Sealer



Description

Pumadur DD Clear is an aliphatic solvent-based UV resistant polyurethane coating. The cured coating has excellent abrasion and chemical resistance and exhibits excellent weathering properties. The coating is recommended for top-coating decorative systems such as **Mozaico** resin terrazzo, decorative flake systems and **Intrica Fusion** decorative quartz flooring. Due to its solvent resistance, **Pumadur DD Clear Gloss** can be used as an anti-graffiti coating. Check the compatibility with the chosen graffiti remover/solvent by applying a test area.

Note: Although Pumadur DD Clear has excellent UV resistance, the product will not prevent UV light travelling through the coating and affecting non-UV-stable material beneath.

Appearance

Available with a gloss, silk finish.

Dry film thickness

Approximately 60 - 75 µm per coat

Coverage

It is recommended that **Pumadur DD Clear** is applied in a minimum of two coats to minimise variations in finish caused by varying substrates. Additional coats may be required depending on the nature of the substrate and the end use.

Coverage*	m ² /kg
Pumadur DD Clear Topcoat (Gloss)	6 - 7.5
Pumadur DD Clear Topcoat (Silk)	5.9 - 7.4

*Coverage figures given are theoretical. Practical coverage rates may vary due to wastage factors and the type, condition, profile and porosity of the substrate. Prevailing site conditions will also affect the coverage. It is always advisable to apply a test panel of the system if the coverage rate is in doubt, especially on a large project to assess correctly the affect of substrate porosity and texture.

Application Conditions

The ideal ambient, substrate and material temperature range is 15 - 20 °C. Localised heating or cooling equipment may be required outside this range otherwise the surface finish may be impaired. The maximum substrate and atmospheric relative humidity should be 75%. The substrate and uncured floor must be kept at least 3 °C above the dew point to reduce the risk of condensation or blooming on the surface from before priming to at least 48 hours after application.

Surface Preparation

In coatings, there is a tendency for the finish to mirror imperfections in the substrate. Surfaces should be abraded to provide a key and solvent wiped using **Pumasolve**. Refer to the **Resdev Guide to Surface Preparation**. A test area should be used to ensure that **Pumadur DD Clear** is compatible with the substrate.

Cure Schedule at 20 °C *

Working life of full packs	60 minutes
Over-coating time (minimum)	16 hours
Over-coating time (maximum)	36 hours
Light foot traffic	16 hours
Medium duty traffic	48 hours
Full Cure	7 days

If the maximum over-coating time is exceeded the coating should be mechanically abraded thoroughly and re-coated.

* The above cure times are approximate and given as a guide only. These times can vary due to prevailing site conditions. Higher temperatures will shorten working time and lower temperatures will extend cure times.

Pack Size

2.5 kg & 5 kg

Application Instructions

Prior to mixing, the temperature of both components should be between 15 and 20 °C. Add the hardener component to the resin component and mix using a low speed electric mixer (300 - 400 rpm) for at least 3 minutes until homogeneous. Keep the mixing paddle fully submerged to avoid the entrapment of air and scrape the sides and bottom of the vessel several times. Distribute the mixture immediately onto the surface using a solvent resistant short nap lint-free mohair roller. Plan the work area to ensure a constant wet edge and work within the working time of the material. It is imperative that film thickness is kept constant, especially with silk or matt coatings to maintain consistency of appearance. This should be regularly checked using a wet film thickness wheel. Ensure that material is not applied more than once or overlapped in any area and apply in one direction only. If the thickness of the applied material is uneven, the surface may have an uneven appearance due to differences in gloss. Avoid pooling as this will lead to solvent entrapment and uncured areas. Do not apply subsequent coats until the previous coat is cured. This will depend on temperature, atmospheric humidity and degree of ventilation. Adequate ventilation and air movement is necessary.

Resdev Limited

Pumafloor House, Ainleys Industrial Estate
Elland, West Yorkshire, HX5 9JP, England
Tel: +44 (0) 1422 379131
fax: +44 (0) 1422 370943
info@resdev.com
www.resdev.com



Resin Development

Pumadur DD Clear

Page 1 of 2
22/08/2022

If applying by spray, suitable respiratory protective equipment should be worn by all exposed persons.

Cleaning

Regular cleaning is essential to enhance and maintain the life expectancy and appearance of the product. **Pumadur DD Clear** can be easily cleaned using industry standard cleaning chemicals and techniques. Consult your cleaning chemical and equipment supplier for more information. Silk and especially Matt coatings have a tendency to soil quicker than gloss coatings as the surface has a micro-texture.

Health and Safety

Refer to product Safety Data Sheet before use.

Limitations


Do not proceed with application if atmospheric relative humidity is, or is anticipated to be, >75% or if the surface temperature is <3 °C above the dew point. Application should not commence when the substrate temperature or the ambient temperature is, or is anticipated to be < 7°C during the application or within the curing period. The manufacture of **Pumadur DD Clear** is a batch process and despite close manufacturing tolerances, slight variation in gloss may occur between batches. Products from different batches should not be used on the same surface or surfaces close together. If mixed batches are unavoidable, it is best practice to use the different batches only in areas where the colour cannot be directly compared. Touching up should only be attempted using product from the same batch using the same application methods. Product should be reserved specially for this purpose. It is recommended that touching up is carried out up to a break in the floor or surface.

Technical Advice

For further information on this or any other Resdev product, please contact our office.

Note

The information contained in this document, and all further technical advice given is based on our present knowledge and experience. However, it implies no liability or legal responsibility on our part. In particular, no warranty or guarantee of product performance in the legal sense is intended or implied as the conditions of use and the competence of any labour involved in the application are beyond our control. Properties listed are for guidance purposes only. We reserve the right to make any changes according to technological progress or further developments.

Resdev Limited, Pumaflor House, Ainleys Industrial Estate Elland, West Yorkshire, HX5 9JP, England			
		13	DOP RV0055/56/57
EN 13813 SR-B2,0-AR0,5-IR4 Synthetic resin screed material for use internally in buildings not subject to reaction to fire regulations			
Reaction to fire	NPD	Impact resistance	IR4
Release of corrosive substances	SR	Sound insulation	NPD
Water permeability	NPD	Sound absorption	NPD
Wear resistance	AR0,5	Thermal resistance	NPD
Bond strength	B2,0	Chemical resistance	NPD

Resdev Limited

Pumaflor House, Ainleys Industrial Estate
Elland, West Yorkshire, HX5 9JP, England
Tel: +44 (0) 1422 379131
fax: +44 (0) 1422 370943
info@resdev.com
www.resdev.com



Resin Development

Pumadur DD Clear

Page 2 of 2
22/08/2022