Intrica Glitterati / Intrica Illumnia

Highly decorative flake scatter system



Description

Intrica Glitterati and Illumnia are decorative seamless floor systems produced by the combination of resin base coat, coloured vinyl and metallic flakes and clear sealers. The overall finish is a mottled mosaic effect with a slightly textured slip resistant surface (dependant on the size of flake and sealing technique).

Colours Available

Glitterati is available in range of 8 vibrant colours incorporating metallic flakes.

Illumnia is available in a range of 6 delicate shades incorporating pale silver and rich gold metallic flakes.

Typical Installations

Intrica Glitterati and Illumnia floor finishes are suitable for use in light to medium duty areas where both hygiene and aesthetics are of paramount importance e.g. showrooms, leisure and commercial environments.

System Build

Refer to individual product technical datasheets for further information.

Approximately 1 mm thickness		
Product	Kg/m2	
Pumaprime SF	0.125	
Pumatect	0.375	
Flake Broadcast	0.65	
Pumatect Clear	0.20 - 0.25	
Pumadur DD Clear	0.08 - 0.12	

Approximately 3 mm thickness	
Product	Kg/m2
Pumaprime SF	0.125
Pumaflow	3.60 (minimum)
Pumatect	0.375
Flake Broadcast	0.65
Pumatect Clear	0.20 - 0.25
Pumadur DD Clear	0.08 - 0.12



These coverage rates are given as a guide only and may vary dependant on substrate surface profile, site conditions, application techniques and wastage. Where the substrate is highly profiled or porous, allow for additional materials.

Flake Application

The decorative flakes should be broadcast to excess into the wet epoxy coating. Once cured, The excess flakes should be swept away and the area de-nibbed to remove sharp edges. The surface should then be vacuumed thoroughly to remove dust and loose flakes before applying the seal coats.

General Maintenance

Intrica Glitterati and Illumnia can be easily cleaned using industry standard cleaning chemicals and techniques designed for epoxy and polyurethane resin flooring. Test cleaning agents prior to use. Do not steam clean or subject to temperatures in excess of 60 °C.

Precautions

Remove food products from the area during application and curing. As will all paint finishes, scratching of the surface may occur with use due to surface contamination and abrasion. In common with all smooth floor finishes, the floor may become slippery under certain conditions.

Technical Advice

For further information on this or any other Resdev product, please contact our office.



Pumaflor House, Ainleys Industrial Estate Elland, West Yorkshire, HX5 9JP, England

Tel: +44 (0) 1422 379131 fax: +44 (0) 1422 370943 info@resdev.co.uk www.resdev.co.uk



Resin Development