

Pumadur HPQ



Product Description:

Pumadur HPQ is a 4 part, coloured quartz system produced by fully broadcasting aggregate onto the **Pumadur HPQ** polyurethane screed base and sealing with **Pumadur PAS Clear**. (see separate datasheet).

Pumadur HPQ has a lightly textured finish which makes the product ideal for both wet and dry processing environments such as the food and beverage industry and commercial areas where a robust, decorative floor is required.

Appearance:

Seamless, multi-coloured surface with a light slip resistant texture.

Features & Benefits:

- Resin rich, easier and quicker to apply than trowel applied screeds.
- Seamless surface.
- Decorative.

Thickness:

6.0 mm - 9.0 mm.

Health & Safety:

Refer to product Safety Data Sheet before use.

Technical Advice:

For further information on this or any other Resdev product, please contact our office.

Available Colours:

Please see price list for available colours.

Surface Preparation:

Inadequate preparation will lead to loss of adhesion and failure. Grinding, light vacuum-contained shot-blasting or planing is recommended. Percussive scabbling or acid etching is not recommended. Anchorage grooves should be cut to a width and depth of twice the thickness of the floor finish at the edges, bay joints, up-stands, drains, doorways and at regular points across the floor, and all debris removed.

Refer to the Resdev Guide to Surface Preparation for further information. For concrete bases in contact with the ground, a damp proof membrane should have been incorporated into the slab design, in accordance with the requirements of CP102 (Code of Practice for Protection of Buildings Against Water from the Ground).



Application Conditions:

Optimum substrate temperature range is 15 - 25 °C. Localised heating (electric powered warm air blower) or cooling equipment may be required outside this range to achieve ideal temperature conditions. The aggregates and fillers can be stored in a cool area (or warm area in the case of low ambient temperature) in order to control product temperature and working life. The substrate and uncured floor must be kept at least 3°C above the dew point to reduce the risk of condensation or blooming on the surface, from before priming, to at least 48 hours after application.

Application:

Priming should be carried out using **Pumaprime SF**, taking particular care to prime, but not fill anchor grooves. (see separate datasheet). Prior to mixing, the temperature of the four components must be between 15 and 25 °C. Pre-mix the coloured resin component before use. Add the hardener component to the coloured resin component and mix using a low speed electric mixer (300 - 400 rpm) for 1 - 2 minutes until homogeneous. Decant the mixture into a rotary drum mixer and add the filler component in stages, mixing for a minimum of 3 minutes until a uniform coloured, lump-free mix is obtained. Apply to the required thickness using a steel float. Ensure that anchor grooves are fully wetted out with material.

Whilst still wet, fully broadcast with 0.4 - 0.8 mm or 0.7 - 1.2 mm quartz at a rate of 4.0 - 5.0 kg per m². When cured, remove excess aggregate using a brush and vacuum. Apply **Pumadur PAS Clear**:

0.35 - 0.40 kg per m² over 0.4 - 0.8 mm quartz.

0.45 - 0.50 kg per m² over 0.7 - 1.2 mm quartz.

When cured, apply **Pumadur DD Clear Silk** if a silk finish is required.

Cleaning:

Regular cleaning is essential to enhance and maintain the life expectancy, slip resistance and appearance of the floor. **Pumadur HPQ** can be easily cleaned using industry standard cleaning chemicals and techniques. Consult your cleaning chemical and equipment supplier for more information. **When fully cured Pumadur HPQ can be cleaned up to 60°C.**

Limitations:

Do not proceed with application if atmospheric relative humidity is, or is anticipated to be, >85% or if the surface temperature is <3 °C above the dew point. Application should not commence when the substrate temperature or the ambient temperature is or is anticipated to be <10 °C during the application or within the curing period.

The design strength of concrete surfaces must be a minimum of 25 N/mm² compressive strength at 28 days. The manufacture of **Pumadur HPQ** is a batch process and despite close manufacturing tolerances, colour variation may occur between batches. Products from different batches should not be used on the same surface or surfaces close together.

If mixed batches are unavoidable, it is best practice to use the different batches only in areas where the colour cannot be directly compared. Touching up should only be attempted using product from the same batch using the same application methods. Product should be reserved specially for this purpose. It is recommended that touching up is carried out up to a break in the floor or surface.

EU Directive 2004/42/EC:

Complies with category j type SB (< 500 g/l).

Pumadur systems are not colour fast and may yellow over time. The rate of change will depend on UV light and heat levels and cannot be predicted. This will be more pronounced on lighter colours but does not affect the performance of the product.

PRODUCT INFORMATION			
Chemical Type	Decorative Polyurethane Screed System		
Packaging: (Pumadur HPQ)	26.00kg Unit:	Resin:	2.90kg
		Hardener:	2.40kg
		Filler:	20.70kg
	Then fully broadcast with the required quartz at: 4.0 - 5.0 kg per m².		
Packaging: (Pumadur PAS Clear)	Unit Size:	2.50kg:	5.00kg:
	Resin:	1.46kg	2.92kg
	Hardener:	1.04kg	2.08kg
Shelf life	Resin & Hardener:	12 Months	
	Aggregate:	6 Months	
Storage conditions	Pumadur HPQ must be stored off the ground in original packaging, unopened and undamaged. The ambient conditions must be dry and between 10°C and 30°C with no direct sunlight. Protect from frost.		

APPLICATION INFORMATION

Mixing Ratio	MIX FULL UNITS
Consumption: (Pumadur HPQ)	Approx. 2.00 kg/m ² per mm. 12 kg/m ² at 6.0 mm. 18 kg/m ² at 9.0 mm.
Consumption: (Pumadur PAS Clear)	0.35 - 0.40 kg per m ² over 0.4 - 0.8 mm quartz. 0.45 - 0.50 kg per m ² over 0.7 - 1.2 mm quartz.
Environmental Conditions	Air Temp +15°C to 25°C Relative air humidity <85% Dew Point >3°C above
Substrate Temperature	+15°C to 25°C
Substrate Moisture Content	No ponding water Substrate relative humidity (RH): <75% Concrete must have a tensile strength: >1.5 N/mm ²
Pot life (approx.)	+10°C 20 to 30 minutes +20°C 15 to 20 minutes +30°C 10 to 13 minutes
Curing Schedule 20°C	Light Pedestrian Traffic Above 12 hours Light Wheeled Traffic Above 24 hours Heavy Duty Traffic Above 48 hours Full Chemical Resistance 7 days
Service Conditions	When fully cured Pumadur HPQ can be cleaned up to 60°C. (once sealed).

TECHNICAL INFORMATION *

Adhesive strength to concrete	BS EN 13892-8 >1.5 N/mm ²
Slip Resistance	Pendulum Test BS 7976-2 ≥ 65 dry & 55 wet
FeRFA Floor Type	BS 8204-6 Type 8

*The typical physical properties given above are derived from testing in a controlled laboratory environment. In the field results may vary due to site conditions.

APPROVALS & STANDARDS

Synthetic Resin Screed material according to EN 13813:2002

Pumadur HPQ is a non-tainting product in accordance with test method TES-S-002 performed by Camden Food Research

Eurofins Indoor Air Quality GOLD certified

Note: The information contained in this document, and all further technical advice is given based on our present knowledge and experience. However it implies no liability or legal responsibility on our part. In particular, no warranty or guarantee of product performance in the legal sense is intended or implied as the conditions of use and the competence of any labour involved in the application is beyond our control. Properties listed are for guidance purposed only. We reserve the right to make any changes according to technological progress or further developments.

Resdev Limited, Pumaflor House, Ainleys Industrial Estate Elland, West Yorkshire, HX5 9JP, England			
CE		13	DOP RV0082
EN 13813 SR-B1,5 Synthetic resin screed material for use internally in buildings not subject to reaction to fire regulations			
Reaction to fire:	NPD		Impact resistance: NPD
Release of corrosive substances :	SR		Sound insulation: NPD
Water permeability:	NPD		Sound absorption: NPD
Wear resistance:	NPD		Thermal resistance: NPD
Bond strength:	B1,5		Chemical resistance: NPD